

# laminates

## CANEVASIT PF CC 201

► **High Pressure Laminate for high mechanical stresses**

► **Standard type**

### General description

Canevasit PF CC 201 is a cotton laminate bonded with phenolic resin.

### RoHS Directive

Hazardous products listed in the EU-directive 2002/95/CE (ROHS-directive), §4 section 1, are not used as ingredients in this material.

### Specifications

IEC/DIN EN 60893 PF CC 201  
DIN 7735 HGW 2082 (\*)  
BS 2572 F3  
NF C 150-C  
NEMA C  
VSM S-PF CC 1

(\*) no longer valid since March 2003

### Colour

Brown

### Application

Guide and stop ledges  
Slide bars  
Ground plates  
Bearings  
Slides for compressors / vacuum pumps  
Cogwheels module 1-2

### Former denominations

HGW F-HW  
Canevasite 62.140  
Canevasit 410.10

### Form of delivery

Sheet formats 2200 x 1220 and 2050 x 1050 mm  
Tolerance of formats +/- 20 mm  
Thickness in range of 0,5 to 100 mm  
Thickness tolerances acc. to DIN EN 60893-3-4

Material also available as cut to size panels and machined parts.  
Other dimensions and thicknesses on request.

### Processing

Machining with carbide or diamond tools.

		Value	Test norm
<b>Mechanical properties</b>			
Flexural strength	MPa	120	ISO 178
Modulus of elasticity	MPa	6000	ISO 178
Edgewise notched impact strength Charpy	kJ/m <sup>2</sup>	10	ISO 179
<b>Electrical properties</b>			
Insulation resistance after the immersion in water	Ω	2.00E+6	IEC 60167
Breakdown voltage //, 90°C in oil	kV	5	IEC 60243-1
Flatwise electric strength, 90°C in oil	kV/mm	0.5	IEC 60243-1
<b>Thermal properties</b>			
Temperature index (TI)	°C	120	IEC 60216
Thermal conductivity	W/m.K	0.2	DIN 52612
Coefficient of linear expansion //	1.0E-6 / K	18	VDE 0304
<b>Physical properties</b>			
Density	g/cm <sup>3</sup>	1.35	ISO 1183
Water absorption 24h 23°C	mg / %	200 / 1.0	ISO 62

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the affiliated companies of Von Roll Holding Ltd. (underneath referred as Von Roll). Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Von Roll does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Von Roll expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Von Roll makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Von Roll shall in no event be liable for incidental, exemplary, punitive or consequential damages.