

# laminates

## DELLIT PF CP 201

► **High Pressure Laminate with good mechanical properties for normal electrical stresses**

► **Standardtype**

### General description

Dellit PF CP 201 is a paper laminate bonded with phenolic resin.

### RoHS Directive

Hazardous products listed in the EU-directive 2002/95/CE (ROHS-directive), §4 section 1, are not used as ingredients in this material.

### Specifications

IEC/DIN EN 60893	PF CP 201
DIN 7735	HP 2061 (*)
BS 2572	P1
NFC 26-150	P
NEMA LI-1	X / XP
VSM	S-PF CP 1

(\*) no longer valid since March 2003

### Colour

Brown or black

### Application

Electrical insulation  
Electrical insulation at low voltage  
Punched parts  
Drilling templates  
Assembly plates

### Former denominations

HP HW  
Pertinax 61.130 / 61.140  
Dellit 400.05

### Form of delivery

Sheet formats 2440 x 1220 and 2050 x 1050 mm  
Tolerance of formats +/- 20 mm  
Thickness in range of 0,5 to 120 mm  
Thickness tolerances acc. to DIN EN 60893-3-4

Material also available as cut to size panels and machined parts.  
Other dimensions and thicknesses on request.

### Processing

Machining with carbide tools.

	Value	Test norm
<b>Mechanical properties</b>		
Flexural strength	MPa 150	ISO 178
Modulus of elasticity	MPa 8000	ISO 178
<b>Thermal properties</b>		
Temperature index (TI)	°C 120	IEC 60216
Thermal conductivity	W/m.K 0.2	DIN 52612
Coefficient of linear expansion //	1.0E-6 / K 20	VDE 0304
<b>Physical properties</b>		
Water absorption 24h at 23°C (10mm thick)	mg / % 100 / 0.9	ISO 62
Density	g/cm³ 1.39	ISO 1183
<b>Electrical properties</b>		
Insulation resistance after the immersion in water	Ω 1.00E+7	IEC 60167
<b>Other properties</b>		
Punchable up to 2 mm thickness at 23°C	2.5	DIN 53488

The product properties set forth in this data sheet are based on the results of testing of typical material produced by the affiliated companies of Von Roll Holding Ltd. (underneath referred as Von Roll). Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Von Roll does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Von Roll expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Von Roll makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Von Roll shall in no event be liable for incidental, exemplary, punitive or consequential damages.